

African Pegmatite (Pty) Ltd
 27 Van Der Bijl Street,
 PO Box 598, Meyerton 1960
 Gauteng, South Africa
 Email: wenger@pegmatite.co.za
 reception@pegmatite.co.za
 Website: www.mineralmilling.com

Tel: +27 016 362 0600/1/2/3/4
 Int: +27 16 362 0600
 Fax: 016 362 1239

MILLERS & PROCESSORS OF BASE MINERALS




Approved By:
 Compiled By: Y ORLANOV

Doc No. : DSC 020
 Rev No. : 02

Date: 25 February 2009
 Page 1 of 1

Data Sheet



Product: Chrome Sand
Grades: AFS 45-55

CHEMICAL ANALYSIS %

Typical: Cr2O3 46% MIN
 SiO2 1%max

PHYSICAL PROPERTIES:

Screens:	AFS	45-55	GRANULOMETRY %
	Moisture	< 0.1%	+ 1700 = 0.00
			+ 850 = 0.08
			+ 600 = 2.57
			+ 425 = 16.48
			+ 300 = 30.17
			+ 212 = 23.03
			+ 150 = 15.06
			+ 106 = 9.14
			+ 75 = 2.37
			+ 53 = 0.67
			- 53 = 0.43

APPLICATION:

Foundry

PACKING:

Packed in 1 ton bags

The information and recommendations in this product data sheet are based on data we believe to be reliable. They are offered in good faith, but do not imply any warranty or performance guarantee, as conditions and methods of use of our products are beyond our control. As such, African Pegmatite Company South Africa makes no express or implied warranties of any kind with respect to this product, including but not limited to any implied warranty of merchantability or fitness for a particular purpose. We recommend that the user determine whether the products and the information given are appropriate, and that the suitability and performance of our products are appropriate by testing with its own equipment. Specifications are subject to change without notice. The information and recommendations given in this product data sheet should not be understood as a recommendation for the use of our products in violation of any patent or as a license to use any patents of the African Pegmatite Company South Africa.

Tel: +27 16 362-0600/4 Fax: +27 16 362-1239 Website: www.mineralmilling.com

