

African Pegmatite (Pty) Ltd
27 Van Der Bijl Street,
PO Box 598, Meyerton 1960
Gauteng, South Africa
Email: wenger@pegmatite.co.za
reception@pegmatite.co.za
Website: www.mineralmilling.com

Tel: +27 016 362 0600/1/2/3/4
Int: +27 16 362 0600
Fax: 016 362 1239

MILLERS & PROCESSORS OF BASE MINERALS



Approved By:
Compiled By: J Sowerby

Doc No. : DSG003
Rev No. : 01

Date: 22 November 2006
Page 1 of 1

Data Sheet



Product : Glass Powder
Grades : Fine Grade

CHEMICAL ANALYSIS %

Typical:	Fe₂O₃	0.33%	Cr₂O₃	0.13%	SiO₂	73.4%
	K ₂ O	0.11%	P ₂ O ₅	0.01%	Na ₂ O	12.6%
	Al ₂ O ₃	0.5%	MgO	3.9%		
	S	0.08%	CaO	8.85%		

PHYSICAL PROPERTIES:

Particle Size	+ 150 µm	< 1.0 %
Bulk Density	1.4 gms/cm ³	

APPLICATION:

Widely used in the foundry industry as a formulation in fluxes and in the manufacture of tundish liners.

PACKING:

Packed in 40-kilogram 3-ply paper bags on pallets or 1 ton bulk bags.

The information and recommendations in this product data sheet are based on data we believe to be reliable. They are offered in good faith, but do not imply any warranty or performance guarantee, as conditions and methods of use of our products are beyond our control. As such, African Pegmatite Company South Africa makes no express or implied warranties of any kind with respect to this product, including but not limited to any implied warranty of merchantability or fitness for a particular purpose.

We recommend that the user determine whether the products and the information given are appropriate, and that the suitability and performance of our products are appropriate by testing with its own equipment. Specifications are subject to change without notice.

The information and recommendations given in this product data sheet should not be understood as a recommendation for the use of our products in violation of any patent or as a license to use any patents of the African Pegmatite Company South Africa.

Tel: +27 16 362-0600/4 Fax: +27 16 362-1239 Website: www.mineralmilling.com

